


## 31575 CLEAR SOFT MATT TH



1000 ml +  
200 ml +  
200 ml



Ø 1.2-1.4 mm  
3.5-4 Atm  
N° coats: 2-3



Low bake at 80°C :  
45'

Pot life at 20°C:  
4 h

### DESCRIPTION

Two-pack polyurethane matt clearcoat with soft-touch effect.

### USE

Soft clearcoat suitable for car interiors and interior applications in general. Applicable directly on PC and ABS.

### CHARACTERISTICS

- Easy to apply
- Uniform velvet feel and soft-touch effect
- Scratch resistant film

### SUBSTRATE PREPARATION

**ABS** and **PC**: Degrease with 00617 PLASTIC CLEANER.

Surfaces painted with solid, metallic and mica matt basecoat derived from 29925 as well as metallic and mica matt basecoat derived from 29945.

### APPLICATION

Spraying.

#### Mixing ratio:

31575 CLEAR SOFT MATT TH  
00271 SOFT LPL HARDENER  
00622 DILUENTE AB/CM

#### weight/volume

1000 parts  
200 parts  
200 parts

Pot life at 20°C: 4 h

Spray viscosity : 34" FORD Cup 4

Ø Air cap: 1.2-1.4 mm

Air pressure: 3.5-4 Atm

N° of coats: 2-3

Recommended film thickness: 40-50 µ

Application conditions : 20-25°C 50-70% R.H.

Theoretical coverage: 1 kg mixture: 8 m<sup>2</sup> at 50 µ

V.O.C. of the mixture ready for use = 564 g/l

---

## **DRYING TIME**

Flash-off: 15' at 20°C  
Low bake: 45' at 80°C

---

## **TECHNICAL DATA**

Solids content ASTM D 1644: 48% parts by weight  
Hardness ASTM D 1522: 50 Oscillations  
Gloss 60° ASTM D 523: 1/1.5 Gloss

---

## **NOTES**

The SOFT finishes are in compliance with the specifications of interior car parts painting. They are used to give the substrates a good appearance and to protect them from polluting agents. They can be critical because of their dirt retention, which prevents from restoring the original aspect. It is necessary to previously evaluate the suitable product use and the limits of its chemical resistance, depending on chemical substances, temperature, type of contacts, etc.

**TECHNICAL DATA SHEET N° 0598-GB**  
**UPDATED 10/2018**

All information contained in this data sheet is the result of carefully controlled tests and is correct to the best of Lechler's knowledge at the time of issue. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user. FOR PROFESSIONAL USE ONLY.