



ISOLANTE EFFETTO NATURALE



1000 g



14-16" FC4 spray



Ø 1,6 – 1,8 mm
N° coats: 1
Pressure: 3/4 bar



Air drying at 25°C
Tack-free: 30 minutes
Through-drying: 1 day

Low baking at stages
at temperatures
from 20 to 50°C

DESCRIPTION

Natural effect isolator.

USE

Suitable for light types of wood whose final effect must be natural without any colour change.

CHARACTERISTICS

- Excellent insulating power
- Very good grain wetting
- Very good transparency
- Ready for use

SUBSTRATE PREPARATION

Application on wooden manufactured items suitably smoothed.

APPLICATION

- Spray, airless and airmix.

Mixing ratio:

I8957 ISOLANTE EFFETTO NATURALE

weight and volume

1000 parts

Ready-for-use product

Spray viscosity at 20°C: 14-16" FC4 spray

Ø Air cap by spray: 1,6 – 1,8 mm

Spray pressure: 3,0-4,0 bar

N° of coats: one coat

Quantity of the applied product: 80-90 g/m²

DRYING TIMES

Air drying at 25°C and RH < 65%:

Dust-free: 15 min.

Tack-free: 30 min.

stackable: 4 hours

Through-drying: 1 day

Low baking:

Suitable for low baking at stages at temperatures from 20°C to 50°C



RECOMMENDED PAINTING PROCESS

Wooden substrates of various types
Substrate sanding with papers P100-P150-P180
Application of ISOLANTE EFFETTO NATURALE
AFTER AT LEAST 90 MINUTES
Polyurethane or acrylic (not polyester nor UV) basecoat application
Basecoat sanding with papers P320-P400
Topcoat application

TECHNICAL DATA SHEET N° W2002-GB
UPDATED 02/2016

All information contained in this data sheet is the result of carefully controlled tests and is correct to the best of Lechler's knowledge at the time of issue. Since conditions of use are beyond the control of the manufacturer, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use contemplated and the manner of use is the sole responsibility of the user. FOR PROFESSIONAL USE ONLY.